

Section 1 - General Description

Item		Guide line	Standard
K value		66-68	67
Quantity of impurities and foreign matters pieces (\leq)		Top grade:16 First grade:30	12
Weight fraction of moisture and volatiles %, (\leq)		Top grade:0.40 First grade:0.40	0.09
Bulk density g/ml (\geq)		Top grade:0.45 First grade:0.42	0.55
Fish eye' defects IN 400C m ² (\leq)		Top grade:20 First grade:40	14
VCM residuals μ g/g (\leq)		Top grade:8 First grade:10	1
A residue after sieving on a sieve with mesh size:	0.25m (\leq) %	Top grade:2.0 First grade:2.0	0.4
	0.063mm (\geq) %	Top grade:90 First grade:90	99
Plasticizer absorption rate, g/100g of PVC (\geq)		Top grade:20 First grade:19	21
Colour (\geq)		78	87
Conclusion		Top grade	